

FGF PC GF

FGF PC GF is suitable for higher demanding applications, requiring a rigid and strong material in combination with a higher temperature resistance. Autoclavable at 121&134°C

Material features:

- High stiffness
- Easy to print
- High tensile strength
- High heat resistance

Colours:

Colours on request. Ask your accountmanager.

Packaging:

FGF PC GF is available in 20kg bag

Drying	4hr,120°C. <200ppm
Zone 1 Temperature	260±20 °C
Zone 2 Temperature	270±20 °C
Zone 3 Temperature	280±20 °C
Mass temperature	260-280°C
Die temperature	280±20 °C

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,4 g/cc
MFR 260°C/5 kg	ISO 1133	12 g/10min
Tensile Strength at Yield	ISO 527	117 MPa
Tensile Strength at Break	ISO 527	118 MPa
Elongation-Strain at Yield	ISO 527	2%
Elongation-Strain at Break	ISO 527	2%
Tensile modulus	ISO 527	9100 MPa
Impact strength - Charpy notched 23°C	ISO 179	10 kJ/m ²
Vicat softening temperature B50	ISO 306	146°C
Heat deflection temperature A	ISO 75	138°C
Mold shrinkage	Internal method (ISO 294-4 based)	0,26%

Additional info:

Please consider the use of a hardened steel nozzle and, if used, a gear pump, when printing with PC GF. The glass fibers are abrasive and will result in fast wear of brass nozzles.

Storage: Cool and dry (15-25°C) and away from UV light.

The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application.